



# TECHNICAL DATASHEET

<b>PRODUCT NAME:</b>	CARBON BLACK
<b>GRADE:</b>	Teknoir <sup>®</sup> S7
<b>COLOR INDEX:</b>	PIGMENT BLACK 7
<b>CAS NO.:</b>	1333-86-4
<b>EINECS NO.:</b>	215-609-9

Properties	Data	Standard Regulation
<b>Bet Surface Area (m<sup>2</sup>/g)</b>	65±10	ASTM/D6556
<b>DBP Absorption (Cc/100g)</b>	210±10	ASTM/D2414
<b>Tint Strength Vs Irb#3 (%)</b>	120±10	ASTM/D3265
<b>Loss Of Heating (Max%)</b>	≤1	ISO1126
<b>Ash Contents (Max%)</b>	≤0.5	ASTM/D1506
<b>Volatile Content (%)</b>	≥0.5	DIN 53552
<b>Residues On 45µm (Ppm Max%)</b>	≤50	ISO 1437
<b>pH</b>	8±0.5	ASTM/D1512
<b>Physical Form</b>	Bead	Visual inspection

**\*RECOMMEND APPLICATION:** Antistatic material, Conductive Products, Conductive Coatings, Conductive Inks, etc

**\*Packing:** 15kgs 3-ply paper bags of Powder form on wood pallet

**\*Loading Volume of 1 X 20'FCL:** 9.0mt in 15kgs paper bags of Bead form

Note: This data is provided for reference only, detailing basic physicochemical properties of the product. Final performance must be tested and adjusted according to your intended application.

