


# Color Difference Report

Specimen Information		
	Standard	Sample
Name	Prin***U	PCnoir®5317
Material		
Condition	Φ4mm, SCE, UV Cut None	Φ4mm, SCE, UV Cut None
Date Time	4/7/2026 1:29:21 PM	4/7/2026 1:33:33 PM



### Tolerance

	ΔE*ab
D65/10°	1.000
A/2°	1.000
F2/2°	1.000

### Color Indexes

		L*	a*	b*	Sum of K/S	MY Carbon
D65/10°	Standard	3.55	0.10	-0.04	--	240.55
	Sample	3.80	0.03	-0.04	93.85	237.64
A/2°	Standard	3.56	0.11	-0.02	--	240.44
	Sample	3.80	0.04	-0.03	93.85	237.62
F2/2°	Standard	3.55	0.10	-0.09	--	240.50
	Sample	3.79	0.01	-0.02	93.85	237.67

### Color Diff.

	ΔL*	Δa*	Δb*	ΔE*ab	Judgement
D65/10°	0.25	-0.06	0.00	0.25	Pass
A/2°	0.24	-0.07	-0.01	0.25	Pass
F2/2°	0.24	-0.09	0.07	0.27	Pass

Test: Alfred      Audit: Karry  
 Instrument Model: X-rite Ci64