


Color Difference Report

| Specimen Information | | |
|----------------------|------------------------|------------------------|
| | Standard | Sample |
| Name | Prin***U | PCnoir®5319 |
| Material | | |
| Condition | Φ4mm, SCE, UV Cut None | Φ4mm, SCE, UV Cut None |
| Date Time | 4/7/2026 1:29:21 PM | 4/7/2026 1:34:57 PM |



Tolerance

| | ΔE*ab |
|---------|-------|
| D65/10° | 1.000 |
| A/2° | 1.000 |
| F2/2° | 1.000 |

Color Indexes

| | | L* | a* | b* | Sum of K/S | MY Carbon |
|---------|----------|------|------|-------|------------|-----------|
| D65/10° | Standard | 3.55 | 0.10 | -0.04 | -- | 240.55 |
| | Sample | 3.45 | 0.05 | -0.09 | 102.64 | 241.77 |
| A/2° | Standard | 3.56 | 0.11 | -0.02 | -- | 240.44 |
| | Sample | 3.45 | 0.07 | -0.08 | 102.64 | 241.75 |
| F2/2° | Standard | 3.55 | 0.10 | -0.09 | -- | 240.50 |
| | Sample | 3.44 | 0.02 | -0.09 | 102.64 | 241.87 |

Color Diff.

| | ΔL* | Δa* | Δb* | ΔE*ab | Judgement |
|---------|-------|-------|-------|-------|-----------|
| D65/10° | -0.10 | -0.04 | -0.05 | 0.12 | Pass |
| A/2° | -0.11 | -0.03 | -0.06 | 0.12 | Pass |
| F2/2° | -0.11 | -0.08 | 0.01 | 0.14 | Pass |

Test: Alfred Audit: Kamy
 Instrument Model: X-rite Ci64