


Color Difference Report

Specimen Information		
	Standard	Sample
Name	PCnoir®71	PCnoir®6315
Material		
Condition	Φ4mm, SCE, UV Cut None	Φ4mm, SCE, UV Cut None
Date Time	4/10/2026 9:28:43 AM	4/10/2026 9:31:00 AM



Tolerance

	ΔE*ab
D65/10°	1.000
A/2°	1.000
F2/2°	1.000

Color Indexes

		L*	a*	b*	Sum of K/S	MY Carbon
D65/10°	Standard	5.44	0.08	-0.23	--	221.99
	Sample	4.15	0.23	0.00	130.65	233.82
A/2°	Standard	5.44	0.07	-0.22	--	222.06
	Sample	4.18	0.29	0.07	130.65	233.51
F2/2°	Standard	5.43	0.07	-0.24	--	222.12
	Sample	4.15	0.14	0.07	130.65	233.73

Color Diff.

	ΔL*	Δa*	Δb*	ΔE*ab	Judgement
D65/10°	-1.30	0.15	0.23	1.33	Fail
A/2°	-1.26	0.22	0.28	1.31	Fail
F2/2°	-1.27	0.07	0.31	1.31	Fail

Test: Alfred Audit: Karry
 Instrument Model: X-rite Ci64