


# Color Difference Report

Specimen Information		
	Standard	Sample
Name	PCnoir®71	PCnoir®6316
Material		
Condition	Φ4mm, SCE, UV Cut None	Φ4mm, SCE, UV Cut None
Date Time	4/10/2026 9:28:43 AM	4/10/2026 9:30:38 AM



### Tolerance

	ΔE*ab
D65/10°	1.000
A/2°	1.000
F2/2°	1.000

### Color Indexes

		L*	a*	b*	Sum of K/S	MY Carbon
D65/10°	Standard	5.44	0.08	-0.23	--	221.99
	Sample	4.75	0.11	-0.07	114.63	227.88
A/2°	Standard	5.44	0.07	-0.22	--	222.06
	Sample	4.76	0.17	-0.06	114.63	227.82
F2/2°	Standard	5.43	0.07	-0.24	--	222.12
	Sample	4.74	0.09	-0.02	114.63	227.98

### Color Diff.

	ΔL*	Δa*	Δb*	ΔE*ab	Judgement
D65/10°	-0.69	0.03	0.15	0.71	Pass
A/2°	-0.67	0.10	0.16	0.70	Pass
F2/2°	-0.68	0.02	0.22	0.72	Pass

Test: Alfred      Audit: Karry  
 Instrument Model: X-rite Ci64