


Color Difference Report

Specimen Information		
	Standard	Sample
Name	PCnoir®71	PCnoir®6316
Material		
Condition	Φ4mm, SCE, UV Cut None	Φ4mm, SCE, UV Cut None
Date Time	4/10/2026 9:19:33 AM	4/10/2026 9:22:39 AM



Tolerance

	ΔE*ab
D65/10°	1.000
A/2°	1.000
F2/2°	1.000

Color Indexes

		L*	a*	b*	Sum of K/S	MY Carbon
D65/10°	Standard	52.36	-1.68	-7.74	--	68.90
	Sample	51.94	-1.61	-7.54	102.60	69.70
A/2°	Standard	51.43	-3.89	-8.64	--	70.67
	Sample	51.04	-3.76	-8.40	102.60	71.43
F2/2°	Standard	51.70	-0.69	-9.03	--	70.17
	Sample	51.30	-0.66	-8.79	102.60	70.94

Color Diff.

	ΔL*	Δa*	Δb*	ΔE*ab	Judgement
D65/10°	-0.42	0.06	0.21	0.47	Pass
A/2°	-0.39	0.13	0.24	0.48	Pass
F2/2°	-0.40	0.03	0.24	0.47	Pass

Test: Alfred Audit: Karry
 Instrument Model: X-rite Ci64