


Color Difference Report

| Specimen Information | | |
|----------------------|------------------------|------------------------|
| | Standard | Sample |
| Name | Prin***U | Teknoir®G3 |
| Material | | |
| Condition | Φ4mm, SCE, UV Cut None | Φ4mm, SCE, UV Cut None |
| Date Time | 4/7/2026 1:40:03 PM | 4/7/2026 1:45:56 PM |



Tolerance

| | |
|---------|-------|
| | ΔE*ab |
| D65/10° | 1.000 |
| A/2° | 1.000 |
| F2/2° | 1.000 |

Color Indexes

| | | L* | a* | b* | Sum of K/S | MY Carbon |
|---------|----------|-------|-------|-------|------------|-----------|
| D65/10° | Standard | 61.97 | -1.19 | -1.83 | -- | 51.75 |
| | Sample | 62.22 | -1.30 | -2.01 | 98.43 | 51.33 |
| A/2° | Standard | 61.67 | -1.65 | -2.37 | -- | 52.27 |
| | Sample | 61.89 | -1.83 | -2.59 | 98.43 | 51.90 |
| F2/2° | Standard | 61.78 | -0.69 | -2.25 | -- | 52.08 |
| | Sample | 62.01 | -0.76 | -2.47 | 98.43 | 51.69 |

Color Diff.

| | ΔL* | Δa* | Δb* | ΔE*ab | Judgement |
|---------|------|-------|-------|-------|-----------|
| D65/10° | 0.25 | -0.11 | -0.18 | 0.33 | Pass |
| A/2° | 0.22 | -0.18 | -0.22 | 0.36 | Pass |
| F2/2° | 0.23 | -0.07 | -0.22 | 0.33 | Pass |

Test: Alfred Audit: Karry
 Instrument Model: X-rite Ci64