


Color Difference Report

Specimen Information		
	Standard	Sample
Name	Prin***U	PCnoir®2410
Material		
Condition	Φ4mm, SCE, UV Cut None	Φ4mm, SCE, UV Cut None
Date Time	4/7/2026 1:40:03 PM	4/7/2026 1:45:00 PM



Tolerance

	ΔE*ab
D65/10°	1.000
A/2°	1.000
F2/2°	1.000

Color Indexes

		L*	a*	b*	Sum of K/S	MY Carbon
D65/10°	Standard	61.97	-1.19	-1.83	--	51.75
	Sample	63.04	-1.36	-2.05	93.05	49.98
A/2°	Standard	61.67	-1.65	-2.37	--	52.27
	Sample	62.69	-1.89	-2.66	93.05	50.56
F2/2°	Standard	61.78	-0.69	-2.25	--	52.08
	Sample	62.82	-0.79	-2.52	93.05	50.35

Color Diff.

	ΔL*	Δa*	Δb*	ΔE*ab	Judgement
D65/10°	1.07	-0.17	-0.22	1.10	Fail
A/2°	1.02	-0.24	-0.29	1.09	Fail
F2/2°	1.04	-0.11	-0.27	1.08	Fail

Test: Alfred Audit: Karry
 Instrument Model: X-rite Ci64