


# Color Difference Report

Specimen Information		
	Standard	Sample
Name	Prin***U	PCnoir®2419
Material		
Condition	Φ4mm, SCE, UV Cut None	Φ4mm, SCE, UV Cut None
Date Time	4/7/2026 1:29:21 PM	4/7/2026 1:33:00 PM



### Tolerance

	ΔE*ab
D65/10°	1.000
A/2°	1.000
F2/2°	1.000

### Color Indexes

		L*	a*	b*	Sum of K/S	MY Carbon
D65/10°	Standard	3.55	0.10	-0.04	--	240.55
	Sample	3.06	0.08	-0.12	116.33	247.05
A/2°	Standard	3.56	0.11	-0.02	--	240.44
	Sample	3.06	0.07	-0.10	116.33	247.05
F2/2°	Standard	3.55	0.10	-0.09	--	240.50
	Sample	3.05	0.04	-0.11	116.33	247.11

### Color Diff.

	ΔL*	Δa*	Δb*	ΔE*ab	Judgement
D65/10°	-0.49	-0.02	-0.08	0.50	Pass
A/2°	-0.50	-0.03	-0.08	0.51	Pass
F2/2°	-0.50	-0.06	-0.02	0.51	Pass

Test: Alfred      Audit: Karry

Instrument Model: X-rite Ci64