


Color Difference Report

Specimen Information		
	Standard	Sample
Name	PC®noir 3800	PC®noir 2429
Material		
Condition	Φ4mm, SCE, UV Cut None	Φ4mm, SCE, UV Cut None
Date Time	3/31/2026 10:54:04 AM	3/31/2026 10:54:22 AM



Tolerance

	D65/10°	A/2°	F2/2°
ΔE^*_{ab}	1.000	1.000	1.000

Color Indexes

	D65/10°		A/2°		F2/2°	
	Standard	Sample	Standard	Sample	Standard	Sample
L*	4.16	4.32	4.13	4.29	4.14	4.31
a*	-0.19	-0.12	-0.20	-0.15	-0.16	-0.09
b*	-0.10	-0.15	-0.17	-0.21	-0.08	-0.14
C*	0.21	0.20	0.26	0.26	0.18	0.16
h°	208.99	231.43	218.98	235.35	205.61	238.55
MY Carbon	233.63	232.00	233.95	232.30	233.83	232.18
Sum of K/S	--	96.32	--	96.32	--	96.32

Color Diff.

	D65/10°	A/2°	F2/2°
ΔL^*	0.16	0.16	0.16
Δa^*	0.06	0.06	0.07
Δb^*	-0.05	-0.05	-0.06
ΔE^*_{ab}	0.18	0.18	0.19
Judgement	Pass	Pass	Pass

Test: Alfred Audit: Karry
 Instrument Model: X-rite Ci64