


## Color Difference Report

Specimen Information		
	Standard	Sample
Name	PCnoir®3800	PCnoir®2429
Material		
Condition	Φ4mm, SCE, UV Cut None	Φ4mm, SCE, UV Cut None
Date Time	3/31/2026 11:22:21 AM	3/31/2026 11:22:52 AM



### Tolerance

	D65/10°	A/2°	F2/2°
$\Delta E^*ab$	1.000	1.000	1.000

### Color Indexes

	D65/10°		A/2°		F2/2°	
	Standard	Sample	Standard	Sample	Standard	Sample
$L^*$	48.53	48.54	47.71	47.71	47.95	47.94
$a^*$	-1.44	-1.44	-3.46	-3.49	-0.59	-0.58
$b^*$	-6.96	-7.09	-7.70	-7.84	-8.09	-8.23
$C^*$	7.11	7.23	8.44	8.58	8.11	8.25
$h^\circ$	258.31	258.50	245.84	246.01	265.83	265.94
MY Carbon	76.40	76.39	78.07	78.08	77.59	77.60
Sum of K/S	--	99.95	--	99.95	--	99.95

### Color Diff.

	D65/10°	A/2°	F2/2°
$\Delta L^*$	0.01	-0.01	0.00
$\Delta a^*$	0.00	-0.03	0.01
$\Delta b^*$	-0.13	-0.14	-0.14
$\Delta E^*ab$	0.13	0.14	0.14
Judgement	Pass	Pass	Pass

Test: Alfred      Audit: Karry

Instrument Model: X-rite Ci64