


Color Difference Report

Specimen Information		
	Standard	Sample
Name	PC®noir 1100	PC®noir 3800
Material		
Condition	Φ4mm, SCE, UV Cut None	Φ4mm, SCE, UV Cut None
Date Time	3/31/2026 10:52:03 AM	3/31/2026 10:54:04 AM



Tolerance

	D65/10°	A/2°	F2/2°
ΔE*ab	1.000	1.000	1.000

Color Indexes

	D65/10°		A/2°		F2/2°	
	Standard	Sample	Standard	Sample	Standard	Sample
L*	3.77	4.16	3.72	4.13	3.74	4.14
a*	-0.25	-0.19	-0.31	-0.20	-0.16	-0.16
b*	-0.28	-0.10	-0.38	-0.17	-0.37	-0.08
C*	0.37	0.21	0.49	0.26	0.40	0.18
h°	228.61	208.99	230.46	218.98	246.56	205.61
MY Carbon	237.90	233.63	238.53	233.95	238.31	233.83
Sum of K/S	--	90.07	--	90.07	--	90.07

Color Diff.

	D65/10°	A/2°	F2/2°
ΔL*	0.39	0.41	0.41
Δa*	0.06	0.11	0.00
Δb*	0.18	0.21	0.29
ΔE*ab	0.43	0.48	0.50
Judgement	Pass	Pass	Pass

Test: Alfred Audit: Karry

Instrument Model: X-rite Ci64