


Color Difference Report

Specimen Information		
	Standard	Sample
Name	PC®noirAS	PC®noir B
Material		
Condition	Φ4mm, SCE, UV Cut None	Φ4mm, SCE, UV Cut None
Date Time	3/31/2026 9:54:27 AM	3/31/2026 10:50:03 AM



Tolerance

	D65/10°	A/2°	F2/2°
ΔE*ab	1.000	1.000	1.000

Color Indexes

	D65/10°		A/2°		F2/2°	
	Standard	Sample	Standard	Sample	Standard	Sample
L*	2.79	2.82	2.75	2.76	2.76	2.78
a*	-0.15	-0.21	-0.19	-0.30	-0.13	-0.13
b*	-0.24	-0.43	-0.29	-0.52	-0.23	-0.53
C*	0.28	0.48	0.35	0.60	0.26	0.55
h°	238.06	244.51	237.37	240.31	241.81	256.47
MY Carbon	250.99	250.53	251.58	251.48	251.44	251.23
Sum of K/S	--	98.63	--	98.63	--	98.63

Color Diff.

	D65/10°	A/2°	F2/2°
ΔL*	0.03	0.01	0.01
Δa*	-0.06	-0.11	0.00
Δb*	-0.20	-0.23	-0.30
ΔE*ab	0.21	0.25	0.30
Judgement	Pass	Pass	Pass

Test: Alfred Audit: Karmy
 Instrument Model: X-rite Ci64