


# Color Difference Report

Specimen Information		
	Standard	Sample
Name	Tek®noirA1	PC®noirAS
Material		
Condition	Φ4mm, SCE, UV Cut None	Φ4mm, SCE, UV Cut None
Date Time	3/31/2026 9:52:53 AM	3/31/2026 9:54:27 AM



**Tolerance**

	D65/10°	A/2°	F2/2°
ΔE*ab	1.000	1.000	1.000

**Color Indexes**

	D65/10°		A/2°		F2/2°	
	Standard	Sample	Standard	Sample	Standard	Sample
L*	2.55	2.79	2.51	2.75	2.52	2.76
a*	-0.09	-0.15	-0.11	-0.19	-0.05	-0.13
b*	-0.28	-0.24	-0.34	-0.29	-0.31	-0.23
C*	0.29	0.28	0.36	0.35	0.31	0.26
h°	252.80	238.06	251.82	237.37	260.95	241.81
MY Carbon	254.98	250.99	255.57	251.58	255.47	251.44
Sum of K/S	--	92.06	--	92.06	--	92.06

**Color Diff.**

	D65/10°	A/2°	F2/2°
ΔL*	0.24	0.24	0.25
Δa*	-0.06	-0.08	-0.08
Δb*	0.04	0.04	0.08
ΔE*ab	0.26	0.26	0.27
Judgement	Pass	Pass	Pass

Test: Alfred      Audit: Karry

Instrument Model: X-rite Ci64