


Color Difference Report

Specimen Information		
	Standard	Sample
Name	FW2**	Teknoir®A1
Material		
Condition	Φ4mm, SCE, UV Cut None	Φ4mm, SCE, UV Cut None
Date Time	3/31/2026 9:28:26 AM	3/31/2026 9:52:53 AM



Tolerance

	D65/10°	A/2°	F2/2°
ΔE*ab	1.000	1.000	1.000

Color Indexes

	D65/10°		A/2°		F2/2°	
	Standard	Sample	Standard	Sample	Standard	Sample
L*	2.25	2.55	2.20	2.51	2.22	2.52
a*	-0.15	-0.09	-0.23	-0.11	-0.12	-0.05
b*	-0.34	-0.28	-0.39	-0.34	-0.37	-0.31
C*	0.37	0.29	0.45	0.36	0.38	0.31
h°	246.12	252.80	239.02	251.82	251.93	260.95
MY Carbon	260.42	254.98	261.31	255.57	261.02	255.47
Sum of K/S	--	87.87	--	87.87	--	87.87

Color Diff.

	D65/10°	A/2°	F2/2°
ΔL*	0.30	0.31	0.30
Δa*	0.06	0.12	0.07
Δb*	0.06	0.05	0.06
ΔE*ab	0.31	0.34	0.31
Judgement	Pass	Pass	Pass

Test: Alfred Audit: Kamy
 Instrument Model: X-rite Ci64