


Color Difference Report

Specimen Information		
	Standard	Sample
Name	FW2**	Teknoir®A2
Material		
Condition	Φ4mm, SCE, UV Cut None	Φ4mm, SCE, UV Cut None
Date Time	3/31/2026 11:12:00 AM	3/31/2026 11:16:45 AM



Tolerance

	D65/10°	A/2°	F2/2°
ΔE*ab	1.000	1.000	1.000

Color Indexes

	D65/10°		A/2°		F2/2°	
	Standard	Sample	Standard	Sample	Standard	Sample
L*	49.24	48.51	48.51	47.85	48.72	48.05
a*	-1.41	-1.34	-3.18	-2.90	-0.62	-0.62
b*	-6.16	-5.44	-6.86	-6.08	-7.15	-6.32
C*	6.32	5.60	7.56	6.74	7.18	6.35
h°	257.09	256.17	245.14	244.53	265.01	264.41
MY Carbon	74.98	76.44	76.46	77.78	76.02	77.38
Sum of K/S	--	104.75	--	104.75	--	104.75

Color Diff.

	D65/10°	A/2°	F2/2°
ΔL*	-0.73	-0.65	-0.67
Δa*	0.07	0.28	0.01
Δb*	0.71	0.77	0.83
ΔE*ab	1.02	1.05	1.07
Judgement	Fail	Fail	Fail

Test: Alfred Audit: Karry
 Instrument Model: X-rite Ci64