

## Test system: Thermoplastic acrylic coating

| Color Paste -Black             |    |
|--------------------------------|----|
| Carbon Black                   | 8  |
| T300 resin                     | 60 |
| XYL:BAC=6: 4                   | 26 |
| BYK163                         | 6  |
| 2–3 mm glass beads             | 70 |
| >>> High shaking for 2.0 hours |    |
| drying agent                   | 1  |
| >>> High shaking for 20min     |    |
| Black paint                    |    |
| Color Paste -Black             | 2  |
| resin varnish                  | 14 |
| Mix well                       |    |

| Tinting            |    |
|--------------------|----|
| Color Paste -Black | 2  |
| white coating      | 15 |
| Mix well           |    |

**Jetness**

PCnoir®3200 VS PCnoir®5319



**Tinting**

PCnoir®3200 VS PCnoir®5319

