


## Test system: Thermoplastic acrylic coating

Color Paste -Black	
Carbon Black	8
T300 resin	60
XYL:BAC=6: 4	26
BYK163	6
2–3 mm glass beads	70
>>> High shaking for 2.0 hours	
drying agent	1
>>> High shaking for 20min	
Black paint	
Color Paste -Black	2
resin varnish	14
Mix well	

Tinting	
Color Paste -Black	2
white coating	15
Mix well	

**Jetness**

PCnoir®6315 VS PCnoir®4510



**Tinting**

PCnoir®6315 VS PCnoir®4510

