

## Test system: Long-oil alkyd coating

Color Paste -Black	
Carbon Black	1.5
Resin varnish	67.5
2–3 mm glass beads	60
>>> High shaking for 2.0 hours	
drying agent	1
>>> High shaking for 20min	
Resin varnish	
Long-oil alkyd resin	75
Xylene	24
Efka4310 (50%)	1
Mix well	

Tinting	
Carbon Black	0.1
Titanium dioxide	9.9
Resin varnish	59
2–3 mm glass beads	60
>>> High shaking for 2.0 hours	
drying agent	1
>>> High shaking for 20min	

**Jetness**

Pri\*\*U VS PCnoir®2410



**Tinting**

Pri\*\*U VS PCnoir®2410

