


Test system:

Two-component acrylic polyurethane coating - automotive refinish paint

| Color Paste - Black | |
|---|------|
| YZ-H755 hydroxy acrylic resin (70%) | 40 |
| Xylene | 12 |
| PMA | 28.8 |
| EFKA4310 (50%) | 11.2 |
| Carbon Black | 8 |
| Total | 100 |
| >>> High shaking for 2.0 hours | |
| Black paint A | |
| YZ-H755 hydroxy acrylic resin (70%) | 20 |
| N-butyl acetate | 2 |
| Xylene | 5 |
| PMA | 3 |
| Black color paste | 10 |
| The ratio of N3390 curing agent to black paint is 1.1 in excess | 11 |
| >>> Stir and mix well | |

| Color matching | |
|---------------------------|-----|
| Color paste- Black | 1 |
| White paint | 9 |
| N3390 | 0.5 |
| >>> Stir and mix well | |

Jetness
PCnoir®3800



Tinting
PCnoir®3800

