


Test system:

Two-component acrylic polyurethane coating - automotive refinish paint

Color Paste - Black	
YZ-H755 hydroxy acrylic resin (70%)	40
Xylene	12
PMA	28.8
EFKA4310 (50%)	11.2
Carbon Black	8
Total	100
>>> High shaking for 2.0 hours	
Black paint A	
YZ-H755 hydroxy acrylic resin (70%)	20
N-butyl acetate	2
Xylene	5
PMA	3
Black color paste	10
The ratio of N3390 curing agent to black paint is 1.1 in excess	11
>>> Stir and mix well	

Color matching	
Color paste- Black	1
White paint	9
N3390	0.5
>>> Stir and mix well	

Jetness
PCnoir®1000



Tinting
PCnoir®1000

